

# Seamless Carbon Steel Line Pipe

ASTM A333 GR6 / ASME SA333 GR6  
Available in single & double random lengths  
Pipe ends bevelled

## SPECIFICATION

Grade 6

Grade : ASTM A333 GR6 / ASME SA333 GR6

Surface finish: Mill protective varnish

### Mechanical Properties

Minimum Tensile Strength      415 MPa      60000 PSI

Minimum Yield Strength      240 MPa      35000 PSI

### Chemical Composition % (max unless otherwise stated)

	Carbon	Manganese	Phosphorus	Sulphur	Silicon	Copper	Chromium	Molybdenum	Nickel	Vanadium	Niobium
Min	0.30	0.29	0.025	0.025	0.10	0.40	0.30	0.12	0.40	0.08	0.02
Max	-	1.06	-	-	-	-	-	-	-	-	-

### Typical Applications

High pressure conveyance pipe for oil, gas, & petrochemicals for low temperature applications.



Kloeckner Metals UK | Head Office  
Valley Farm Road, Stourton, Leeds,  
West Yorkshire, LS10 1SD  
[www.kloecknermetalsuk.com](http://www.kloecknermetalsuk.com)

t: 0113 254 0711  
e: [enquiries@kloeckner.com](mailto:enquiries@kloeckner.com)  
[shop.kloeckner.co.uk](http://shop.kloeckner.co.uk)



@KloecknerUK



Kloeckner Metals UK



Kloeckner Metals UK